Petro Laboratories Inc.

1295 Matheson Blvd. East, Mississauga, Ontario, L4W 1R1 Tel: (905) 361-2388 E-mail: petrolab@gmail.com

Laboratory Report

St. Marys Cement
585 Water Street S,
St. Marys, Ontario
N4X 1B6

Lab no.: 8697 -13 to 16
Date Report: Apr 23, 2025
Sample in: Apr 16, 2025
PO no.: 6300615152

Attention: Kara Pelissero

Re: Petcoke samples from Mar 2025 for analysis.

		Lab no.	8697-13	8697-14	8697-15	8697-16
		Sample ID.	**Petcoke April 8**	**Petcoke April 9**	**Petcoke April 10**	**Petcoke April 11**
Tests	**Method ASTM**	**Unit**	**Results**			
1. Calorific Value, As Received	E870	BTU/lb MJ/kg	13973 32.500	14330 33.331	13890 32.307	14095 32.784
2. Moisture content, As Received	E871	% wt.	0.58	0.71	1.37	1.19
3. Total Carbon, As Received	D3178	% wt.	85.00	85.55	85.15	84.14
4. Sulfur, As Received	D1552	% wt.	4.20	5.09	5.21	5.64
5. Total Organic Carbon	D4129	% wt.	84.02	84.47	84.11	83.21

Tested by : P.S / A.C.(Chemist)

Approved by James Szeto

Member of ASTM
JS:LN

James Szeto,B.Sc.
Chief Chemist