

Petro Laboratories Inc.

1295 Matheson Blvd. East, Mississauga, Ontario, L4W 1R1 Tel: (905) 361-2388

E-mail: petrolab@gmail.com

Laboratory Report

P2 of 5

St. Marys Cement
585 Water Street S,
St. Marys, Ontario
N4X 1B6

Lab no.: 8697 -7 to 12
Date Report: Apr 23, 2025
Sample in: Apr 16, 2025
PO no.: 6300615152

Attention: Kara Pelissero

Re: Wood chips ,Plastic Scraps & Petcoke samples from Mar 2025 for analysis.

			Lab no.	8697-7	8697-8	8697-9	8697-10	8697-11	8697-12
			Sample ID.	BMP April 10	ALCF April 8	ALCF April 9	ALCF April 10	ALCF April 11	Petcoke April 7
Tests	Method ASTM	Unit	Results						
1. Calorific Value, As Received	E870	BTU/lb MJ/kg	9995 23.248	10054 23.385	12311 28.635	12490 29.051	13464 31.317	13722 31.917	
2. Moisture content, As Received	E871	% wt.	2.60	8.30	12.37	7.92	8.81	0.57	
3. Total Carbon, As Received	D3178	% wt.	51.59	57.30	61.46	63.54	71.21	84.61	
4. Sulfur, As Received	D1552	% wt.	0.21	0.19	0.48	0.73	0.54	4.50	
5. Total Organic Carbon	D4129	% wt.	50.41	56.15	60.36	62.41	70.15	83.53	

Tested by : P.S / A.C.(Chemist)

Member of ASTM
JS:LN

Approved by

James Szeto

James Szeto, B.Sc.
Chief Chemist